



Cebos Color Srl
24040 Osio Sopra (BG)
Via dei Dossi, 7
Tel. +39 035 265141
Fax +39 035 2651431
C.F. & P.Iva 02567630161
info@cebos.it
www.ceboscolor.it

Revision No.3
Revision date: 28/11/2022

DATA SHEET DS C.015

CEBOSTONE - CEBOSTONE HB

Description

Water-based acrylic finish for indoor and outdoor use: the particular surface structure allows to realize opaque finishes characterized by delicate chiaroscuro, obtained by the alternation of more sandy and smoother areas. The product is available in two different grain sizes: a fine CeboStone (0.3 mm) and a larger CeboStone HB (0.7 mm) more suitable for use outdoors or on rough surfaces.

Packs available

1 Lt - 5 Lt - 10 Lt

Staining

The product can be coloured with the CeboColorStation tintometric system or with the CeboKit universal dyes in the dosages shown on the colour charts. Different colors are possible from those of the folder, varying the dosages provided and/ or mixing the dyes. Since you have to prepare several packs of the same color it is advisable to use dyes and products with the same batch of production.

Dilution

0 to 5% by volume with water.

Mixing

Mix the product well before use.

Suitable supports

All plaster, lime and civil supports are suitable. Check that the funds are perfectly clean, dry and uniform in appearance and absorption.

Conditions of application

The temperature should be between +5 °F and +30 °F, air humidity below 80%. Direct sun application is not recommended.

Preparation of the supports outside

Apply with short coat roller CeboFix R white diluted to 20-30% by volume with water, in one or two coats until the bottom is completely covered.

Preparation of the supports inside

Apply with short hair roller FondoPlus white diluted to 10% by volume with water, in one or two coats until the bottom is completely covered.

Application

CeboStone is applied in a brush coat, working with crossed brushstrokes in order to obtain on the surface an alternation of rustic and smoother areas.

Application information is contained in videos, folders, and catalogs.

Technical specifications

Drying: 4-6 h

Theoretical yield: 6-8 m²/litre

Physical appearance: Liquid, white

Specific Weight: 1.65 g/cm³

pH: 8.5-9.5

This Data Sheet replaces and cancels all other Data Sheets relating to the product described, drawn up on the previous date. All the information in this Data Sheet derives from our best experience: however, the Data Sheet does not imply any acquisition of responsibility by our Company for applications outside our direct control. Our Technical Department is always at your disposal to provide further information or clarification.

VOC classification (Directive 2004/42/EC)

Product category: Decorative effect paints (1)

Maximum permitted limit (2010) for ready-to-use product 200 g/l

CeboStone contains VOC: 11 g/l

Type of ship IAQ (indoor air quality)

Classification according to the decree of the French Republic N°. 2011-321 of March 2011.

Information on the level of emission of volatile substances into indoor air, which presents a risk of inhalation toxicity, on a class scale ranging from A+ (very low) to C (very high).

Storage

The product has a guaranteed duration of 24 months if stored in original packaging at temperatures between +5 and +35 °C, in a dry and ventilated place, away from the sun's rays and heat sources.

Safety instructions

The product does not require special environmental or personal protective measures; however, it is advisable to avoid prolonged contact with the skin. In case of eye contact, immediately wash the eyes with clean water; if irritation occurs, consult a doctor. The user information is contained in the relevant Safety Data Sheet.